


Overzicht meetresultaten akoestische wandbespanning "Type Soft"

| HERTZ | 125 | 250 | 500 | 1000 | 2000 | 4000 |
|-----------|------|------|------|------|------|------|
| Soft 25A | 0,06 | 0,21 | 0,46 | 0,73 | 0,90 | 0,93 |
| Soft 25R | 0,07 | 0,26 | 0,65 | 0,91 | 1,03 | 1,05 |
| Soft 60A | 0,20 | 0,53 | 0,90 | 1,00 | 1,03 | 1,07 |
| Soft 60R | 0,27 | 0,81 | 1,04 | 1,02 | 1,00 | 0,97 |
| Soft 100R | 0,49 | 0,99 | 1,05 | 1,05 | 1,05 | 1,04 |



| TYPE | Alphaw. | Klasse |
|-----------|---------|--------|
| Soft 25A | 0,45 | D |
| Soft 25R | 0,55 | D |
| Soft 60A | 0,80 | B |
| Soft 60R | 1,00 | A |
| Soft 100R | 1,00 | A |

Meting te KU Leuven
 Verboden gedeeltelijk te reproduceren zonder toestemming